

[Sign in](#)

Google

[Web](#) [Images](#) [Video](#) [News](#) [Maps](#) [more »](#)

(aromatic bischloroformate) and copolymer an

Search

[Advanced Search](#)
[Preferences](#)

The "AND" operator is unnecessary -- we include all search terms by default. [\[details\]](#)

Web Results 1 - 10 of about 64 for (aromatic bischloroformate) and copolymer and phosgene and interfac

Scholarly articles for (aromatic bischloroformate) and copolymer and phosgene and interfacial phase catalyst and solvent and ph



[Scale of cooperative \$\gamma\$ -relaxation of bisphenol A ...](#) - Xiao - Cited by 8

Detecting the endpoint in interfacial aromatic polycarbonate ...

The method of claim 1 wherein the **interfacial** polycarbonate **catalyst** is a ... The organic **solvent** can be any organic liquid which solubilizes **phosgene** and ...
www.freepatentsonline.com/5114861.html - 54k - [Cached](#) - [Similar pages](#)

Process for producing polycarbonates from nitrogen diol and ...

The process of **interfacial** polycondensation using **phosgene** can produce high ... The **aromatic** diol haloformate is also in an organic **solvent** solution. ...
www.freepatentsonline.com/5288836.html - 65k - [Cached](#) - [Similar pages](#)
[[More results from www.freepatentsonline.com](#)]

[PDF] Scale of Cooperative γ -Relaxation of Bisphenol A Polycarbonate

File Format: PDF/Adobe Acrobat

In an **interfacial** polymerization, an. **aromatic bischloroformate** will be hydrolyzed in the ... the freezing of the aqueous **phase**). A. complex **catalyst** ...
pubs.acs.org/cgi-bin/abstract.cgi/mamobx/1992/25/i25/f-pdf/f_ma00051a012.pdf?sessid=600613 - [Similar pages](#)

Thermoplastic resin compositions - US Patent 5455302

Component (B) is a **copolymer** which contains (a) an **aromatic** vinyl monomer ... After washing the organic **solvent phase** three times with 2% hydrochloric acid, ...
www.patentstorm.us/patents/5455302-description.html - 37k - [Cached](#) - [Similar pages](#)

Copolymers of tyrosine-based polyarlates and poly(alkylene oxides) ...

Merrill described the **interfacial** copolymerization of poly(bisphenol-A ... As determined by GPC using THF as the **solvent**, the **copolymer** has a weight average ...
www.patentstorm.us/patents/6048521-description.html - 61k - [Cached](#) - [Similar pages](#)
[[More results from www.patentstorm.us](#)]

[PDF] Interfacial synthesis and characterization of random and segmented ...

File Format: PDF/Adobe Acrobat

The **pH** was decreased to about 9 with addition of. **phosgene**, and the aqueous **phase** was removed from. the reactor with suction. The **copolymer** solution ...
doi.wiley.com/10.1002/app.1994.070520401 - [Similar pages](#)

[PDF] Silicone polycarbonates from new aryl-terminated siloxane precursors

File Format: PDF/Adobe Acrobat

siloxane silicon polycarbonate **copolymer** polycarbonate **interfacial** ... solution at **pH** 9-11 using triethylamine as **phase**. transfer **catalyst**. **Phosgene** was ...
doi.wiley.com/10.1002/pola.1991.080291201 - [Similar pages](#)
[[More results from doi.wiley.com](#)]

[PDF] NONBISPHENOL A POLYCARBONATES *

File Format: PDF/Adobe Acrobat

amine or a **phase transfer catalyst**. **Phosgene** is then added to complete the ... M. Nishiguchi and T. Tokuda, **Aromatic** polycarbonate **copolymer**, a process for ...
taylorandfrancis.metapress.com/index/UJ7P4HWC0D35E2MD.pdf - [Similar pages](#)

Siloxane-containing polymers - Patent Review 4499149

The **phase transfer catalyst** is believed to proceed as follows. ... a poly-basic carboxylic acid, anhydride or acyl halide, **phosgene**, or a **bischloroformate**. ...
www.wikipatents.com/4499149.html - 372k - [Cached](#) - [Similar pages](#)

EP962832 Canon european software patent - Toner, toner production ...

through an **interface** to make analysis, and calculating the data ... an aliphatic or **aromatic bischloroformate** in a methylene chloride **solvent** using pyridine ...
gauss.ffii.org/PatentView/EP962832 - 224k - [Cached](#) - [Similar pages](#)

Result Page: 1 2 **[Next](#)**

Try [Google Desktop](#): search your computer as easily as you search the web.

[Search within results](#) | [Language Tools](#) | [Search Tips](#) | [Dissatisfied? Help us improve](#)

[Google Home](#) - [Advertising Programs](#) - [Business Solutions](#) - [About Google](#)

©2006 Google

[Sign in](#)

Google

[Web](#) [Images](#) [Video](#) [News](#) [Maps](#) [more »](#)

(aromatic bischloroformate) and copolymer an

Search

[Advanced Search](#)
[Preferences](#)The "AND" operator is unnecessary -- we include all search terms by default. [\[details\]](#)**Web** Results 11 - 19 of about 64 for **(aromatic bischloroformate) and copolymer and phosgene and interfa****[PDF] Polycondensation Reactions of Fluorinated Organic Compounds**

File Format: PDF/Adobe Acrobat

chloride as a **catalyst** ... and the **copolymer**), but the thermal stability increases ... with the amide **solvents**, the dichlorides of **aromatic acids** ...www.turpion.org/php/full/infoFT.phtml?journal_id=rc&paper_id=1962&year_id=1971&volume_id=40&a... - [Similar pages](#)**[PDF] The Presidential Green Chemistry Challenge Awards Program Summary ...**

File Format: PDF/Adobe Acrobat - View as HTML

inating the need to manufacture the bisphenol A **bischloroformate** at Kodak in ... menting a novel **phosgene** production **catalyst** (well within the proposed 18 ...epa.gov/greenchemistry/pubs/docs/award_entries_and_recipients1998.pdf - [Similar pages](#)**[PDF] B B R R E E V V E E T T T T T T I e e I I N ...**

File Format: PDF/Adobe Acrobat

within the **pH** range of 6-8. An **interface** layer is applied between the active ... **copolymer** is produced by polymerizing the acrylic monomer in **solvent** using ...www.ticinotransfer.ch/Documenti/pdf/RimanereInformati_Download/RIBEM_NEWS_2006-7.pdf - [Similar pages](#)**Polycarbonates suitable for use in optical articles - Patent ...**If the **interfacial** process is used, the addition of various **phase** transfer ... This process does not require the use of **phosgene** or a **solvent** and minimizes ...www.wikipatents.com/6001953.html - 180k - [Cached](#) - [Similar pages](#)**[PDF] Aliphatic Polyesters: Synthesis, Properties and Applications**

File Format: PDF/Adobe Acrobat

tained (Scheme 1, a). a,w-**Bischloroformate** was then prepared by treating this. oligomer with **phosgene**. Poly(ester-carbonate) (Mn=30000 and Mw=48000) ...www.springerlink.com/index/B18U75BR2YGLTVUV.pdf - [Similar pages](#)**[PDF] Synthesis and Characterization of Cyclic Polymers and ...**

File Format: PDF/Adobe Acrobat

the synthesis of **aromatic** polyethers. [49,50] . **Interfacial** condensation may be used ...The conditions (e.g. **solvent** quality, temperature, solid **phase**) are ...

deposit.ddb.de/cgi-bin/dokserv?idn=975168126&

dok_var=d1&dok_ext=pdf&filename=975168126.pdf - [Similar pages](#)**[PDF] L Y ION -**

File Format: PDF/Adobe Acrobat

The yield of the **aromatic bischloroformate** was somewhat low and was ... filtered off and the **solvent** and excess **phosgene** stripped under. reduced pressure. ...

ntrs.nasa.gov/archive/nasa/casi.ntrs.nasa.gov/19670010667_1967010667.pdf -

[Similar pages](#)**Process for preparing random copolycarbonate**The **pH** of the polymer mixture is reduced to 7 with **phosgene**. The organic and aqueous phases are allowed to separate the aqueous **phase** is removed and the ...

www.donahuesystems.com/nmr_inv/process_preparing_random_copolycarbonate/ -

[Similar pages](#)

Compositions of cyclic oligomers

Although addition of the **bischloroformate** neat (i.e., without **solvents**) is ... Preparation and Polymerization of a 4 mole % Cyclic Oligomers **Copolymer** of ...
www.90minuta.com/inventions/piezo_electronic_horn/compositions_cyclic_oligomers.html -
[Similar pages](#)

In order to show you the most relevant results, we have omitted some entries very similar to the 19 already displayed.

If you like, you can repeat the search with the omitted results included.

Result Page: **Previous** [1](#) [2](#)

Try [Google Desktop](#): search your computer as easily as you search the web.

[Search within results](#) | [Language Tools](#) | [Search Tips](#)

[Google Home](#) - [Advertising Programs](#) - [Business Solutions](#) - [About Google](#)

©2006 Google

EAST Search History

| Ref # | Hits | Search Query | DBs | Default Operator | Plurals | Time Stamp |
|-------|------|---|---|------------------|---------|------------------|
| L1 | 963 | bischloroformate and (diol or dihydroxy) and phosgene | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB | OR | ON | 2006/12/18 09:34 |
| L2 | 494 | bischloroformate and (diol or dihydroxy) and phosgene and ph | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB | OR | ON | 2006/12/18 09:34 |
| L3 | 464 | bischloroformate and aromatic and (diol or dihydroxy) and phosgene and ph | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB | OR | ON | 2006/12/18 09:34 |
| L4 | 192 | bischloroformate and aromatic near4 (diol or dihydroxy) and phosgene and ph | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB | OR | ON | 2006/12/18 09:34 |

EAST Search History

| | | | | | | |
|-----|-----|--|--|----|----|------------------|
| L5 | 185 | bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ph | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:35 |
| L6 | 182 | bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ph and (polycarbonate or polysiloxane) | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:35 |
| L11 | 144 | bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and (acidity or alkalinity or ph) and (polycarbonate or polysiloxane) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:52 |
| L12 | 144 | bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and (acidity or alkalinity or ph) and (polycarbonate or polysiloxane) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:36 |
| L13 | 141 | bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and (polycarbonate or polysiloxane) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:52 |

EAST Search History

| | | | | | | |
|-----|----|--|--|----|----|---------------------|
| L14 | 20 | aromatic near4 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and (polycarbonate or polysiloxane) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:52 |
| L15 | 2 | aromatic near4 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and (polycarbonate near3 polysiloxane) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:53 |
| L16 | 20 | aromatic near4 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and copolymer | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:54 |
| L17 | 17 | aromatic near4 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and copolymer and catalyst | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:54 |
| L18 | 30 | aromatic near10 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and copolymer and catalyst | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:55 |

EAST Search History

| | | | | | | |
|-----|----|--|--|----|----|---------------------|
| L19 | 30 | aromatic near10 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and copolymer and catalyst and solvent | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:55 |
| L20 | 29 | aromatic near10 bischloroformate and aromatic near4 (\$8diol or dihydroxy\$8) and phosgene and ((acidity or alkalinity) near4 value or ph) and copolymer and catalyst and solvent and (phase or interfacial) | US-PGPU B; USPAT; USOCR; EPO; JPO; DERWEN T; IBM_TDB | OR | ON | 2006/12/18 09:55 |